

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



10/539336



(43) International Publication Date  
15 July 2004 (15.07.2004)

PCT

(10) International Publication Number  
WO 2004/058195 A1

(51) International Patent Classification<sup>7</sup>: A61K 6/083,  
C08F 8/44, 222/02

(21) International Application Number:  
PCT/US2003/040658

(22) International Filing Date:  
17 December 2003 (17.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/435,058 20 December 2002 (20.12.2002) US

(71) Applicant (for all designated States except US):  
SMITHKLINE BEECHAM CORPORATION  
[US/US]; One Franklin Plaza, PO Box 7929, Philadelphia,  
PA 19101 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): GASMAN, Robert, C.  
[US/US]; 165 Tunicflower Lane, West Windsor, NJ 08550  
(US).

(74) Agent: WINSLOW, Andrea, L.; Smithkline Beecham  
Corporation, Corporate Intellectual Property, UW2220,  
709 Swedeland Road, P.O. Box 1539, King of Prussia, PA  
19406-0939 (US).

(81) Designated States (*national*): AE, AG, AL, AU, BA, BB,  
BR, BZ, CA, CN, CO, CR, CU, DM, DZ, EC, EG, GD, GE,  
HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV,  
MA, MG, MK, MN, MX, NO, NZ, OM, PH, PL, RO, SC,  
SG, TN, TT, UA, US, UZ, VN, YU, ZA.

(84) Designated States (*regional*): ARIPO patent (BW, GH,  
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,  
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the  
claims and to be republished in the event of receipt of  
amendments

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: DENTURE ADHESIVE

(57) Abstract: Denture adhesive compositions with sufficient initial adhesion to the gums that build up enough cohesive strength upon hydration with saliva to withstand the stresses occurring during food mastication and cushions the gums from contact with the denture during chewing. The adhesive comprises a mixed partial salt of an amino ethyl ethylene urea substituted polyalkylvinylether/maleic acid copolymer wherein the cations of the salt are selected from the group consisting of zinc, calcium, magnesium, strontium, zirconium, sodium, and potassium.

WO 2004/058195 A1

## DENTURE ADHESIVE

### FIELD OF THE INVENTION

This invention relates to denture adhesives and to methods for making and using  
5 denture adhesives. In particular, this invention relates to an amino ethyl ethylene urea-  
substituted mixed partial salt of a copolymer of a polyalkyl vinyl ether and maleic acid,  
(PVE/MA) as a new denture adhesive active.

### BACKGROUND OF THE INVENTION

10 Ordinary removable dentures and dental plates function as a substitute for all or part  
of missing teeth ordinarily found in the mouth. While dentures are usually carefully fitted  
for the user, the fit can change over time, causing discomfort and slippage. In order to  
alleviate the discomfort and to control the slippage, a denture adhesive may be applied to the  
denture. The denture adhesive acts both as an adherent and as a gasket or cushion between  
15 the dentures and the gums of the denture wearer. Denture adhesives are known and can be  
in the form of creams, liquids, powders, and liners, either extruded or with a non-adhesive  
self-supporting layer.

Denture adhesives are designed to provide a diverse range of seemingly  
contradictory properties in an extraordinarily complex environment, i.e., the human mouth.  
20 Denture adhesives must develop a quick tack upon contact with the oral mucosa to prevent  
the denture from coming loose; they must also develop cohesive strength quickly when  
hydrated with moisture or saliva. They must also hold the denture in place for a period of  
time, which may be as long as 12 to 16 hours. Denture adhesives should only need to be  
applied once per day and should be nontoxic and organoleptically acceptable. They must  
25 not be easily washed out, i.e., the adhesive must resist degradation under extreme  
environmental changes occurring in the oral cavity during the course of daily activities, e.g.,  
drinking hot or cold beverages. But, denture adhesives must also easily release from the  
dentures and oral mucosa after use.

Early denture adhesives contained finely ground particles of natural gums that  
30 expanded when wet with water to become a viscous gel, which acted as a cushion and an  
adherent between the dental plate and the gum tissue. These early denture adhesives have  
been supplanted by polymeric denture adhesives.

Several attempts have been made to fashion a denture adhesive using various  
polymer salts. One preferred polymer from the field is a mixed partial salt of a copolymer  
35 of maleic acid and alkyl vinyl ether, sold under the GANTREZ® trade name. This class of

polymers was described as a possible denture adhesive in Germann, et al. U.S. Patent No. 3,003,988, which issued more than 30 years ago.

That patent describes synthetic, water sensitized but water insoluble, materials comprising mixed partial salts of lower alkyl vinyl ether-maleic acid copolymers for stabilizing dentures. The salts mentioned in the patent are a mixture of (a) calcium and (b) sodium, or potassium or quaternary ammonium compounds in a 1:1 to 5:1 molar ratio. The calcium hydroxide and monovalent cation hydroxides are added to an aqueous dispersion of the acid copolymer to form a mixed salt.

The use of this class of materials has been described in a variety of other patents. Examples include U.S. Patent Nos.; 5,830,933; 4,980,391; 4,373,036; 5,006,571; 4,521,551; 3,868,432 and European Published Patent Application No. 406,643.

In order to provide additional adhesive and cohesive properties to denture adhesives made from GANTREZ<sup>®</sup> polymers, one approach has been to manipulate the salt form of the copolymer. Examples can be found in WO 92/22280, WO 92/10988, WO 92/10987, and WO 92/10986.

One approach is found in U.S. Pat. No. 4,758,630 to Shah et al., issued July 19, 1988, which is directed to denture adhesives having mixed partial salts of zinc and strontium.

Another approach is reported in U.S. Pat. No. 5,073,604 to Holeva et al., issued December 17, 1991, which is directed to a denture adhesive made from a partial salt of a GANTREZ<sup>®</sup> copolymer, wherein the cations are zinc ions in combination with calcium or strontium ions in combination with with calcium, and optionally containing sodium cations.

U.S. Pat. No. 5,298,534 to Prosis et al., issued March 29, 1994, reports using GANTREZ<sup>®</sup> salts of calcium, sodium, strontium, zinc, magnesium and potassium with boron cross-linked guar gum and an oil base as a carrier. The preferred mixed salt is a Ca/Na mixed salt. The guar gum is "critical" to the asserted extended holding power and viscosity building properties.

Another approach has been to employ an adhesion adjuvant in the formulation or converting the copolymer into a terpolymer, and examples of these approaches can be found in U.S. Patent Nos. 3,736,274, 5,037,924 and 5,093,387.

Despite the efforts which have been put into improving the properties of maleic anhydride/alkyl vinyl ether type polymers and their salts as useful denture adhesive actives, these formulations do not provide the full desired measure of adhesion, cohesion, agreeable

taste and resistance to washout from beneath the denture. Therefore, there exists a need for improved denture adhesive formulations.

## SUMMARY OF THE INVENTION

5           The principal object of the present invention therefore, is to provide a new and improved denture adhesive composition having an unusually strong affinity for oral tissues and for the acrylic denture, and builds up a cohesive strength for good hold characteristics when hydrated with moisture or saliva so as to be able to resist stresses such as those that occur upon mastication.

10           Another object of the invention is to provide an adhesive in which the improved adhesive retains its adhesive properties for prolonged periods of time and resists wash out. Still another object of the invention is to provide an adhesive that cushions the gums from the denture stresses that develop during the chewing of food.

          Additional objects and advantages of the invention will be set forth in part in the description that follows, and in part will be obvious from this description, or may be learned by practice of the invention. The objects and advantages of the invention may be realized and attained by means of the instrumentalities and combinations particularly pointed out in the appended claims.

15           To achieve the foregoing objects and in accordance with the purpose of the invention, as embodied and broadly described herein, the invention provides a denture adhesive comprising a mixed metal salt containing sodium, and/or calcium, and/or zinc and/or strontium and/or magnesium, and/or potassium cations, of an AEEU-substituted-partial salt of polyalkyl vinyl ether/maleic acid, copolymer.

20           To further achieve the foregoing objects and in accordance with the purpose of the invention, the invention further provides a method for securing a removable dental device in the mouth comprising applying a denture adhesive comprising a mixed metal, AEEU-substituted-partial salt of polyalkylvinyl ether, maleic acid, copolymer. The function of the AEEU substituent in this salt copolymer is to confer on this salt copolymer the property of specific adhesion to the oral tissues and to an acrylic denture.

30

## DETAILED DESCRIPTION OF THE INVENTION

### Brief Description of the Drawings

While this specification concludes with claims particularly pointing out and distinctly claiming that which is regarded as the present invention, the objects and

advantages of this invention may be more readily ascertained from the following description of a preferred embodiment when read in conjunction with the accompanying drawings.

Figure 1 is a chart depicting a dislodge force profile comparison of three denture adhesives creams containing varying adhesive components: (1) Gantrez Salt 418, (2) AEEU substituted at a level of 0.3 molar substitution to Salt 418 and (3) AEEU substituted Salt 418 with the addition of 0.5% S-97 Gantrez acid.

The polymer salts of the present invention are the mixed partial salts of a C<sub>1</sub>-C<sub>4</sub> alkyl vinyl ether maleic acid copolymer. Methyl vinyl ether/maleic anhydride (MVE/MA) which has a specific viscosity larger than 1.2 in methyl ethyl ketone at 25°C., is the preferred starting material copolymer. The anhydride copolymer is mixed with the AEEU at room temperature and then converted to an amide at elevated temperatures, hydrolized to the acid and then neutralized with the appropriate cations. Most preferably, copolymers are selected from the copolymers set forth in U.S. Patent No. 5,525,652, the disclosure of which is incorporated herein by reference. While the copolymers of that invention are the preferred copolymers, this invention is not limited to the use of those copolymers.

Suitable metal salt combinations include, but are not limited to, a mixed salt of sodium/magnesium/zinc, a mixed salt of magnesium/zinc, a mixed salt of zinc/calcium, a mixed salt of calcium/sodium, a mixed salt of calcium/potassium, a mixed salt of calcium/strontium, a mixed salt of calcium/zirconium, a mixed salt of magnesium/strontium, a mixed salt of magnesium/zirconium, a mixed salt of sodium/strontium, a mixed salt of sodium/zirconium, a mixed salt of zinc/strontium, a mixed salt of zinc/zirconium and a mixed salt of magnesium/sodium and the like.

The degree of substitution limits for alkyl vinyl ether/maleic acid (MVE/MA) partial salts of the invention are: (a) from about 5% to about 55% magnesium, more preferably from about 15% to about 45% magnesium, and most preferably from about 20% to about 40% magnesium; (b) from about 5% to about 65% zinc, more preferably from about 10% to about 60% zinc, and most preferably from about 15% to about 55% zinc; and (c) from about 0% to about 40% sodium, preferably from about 0% to about 35% sodium, and most preferably from about 0% to about 30% sodium.

The polymer salt is prepared by the partial neutralization of an aqueous premix of AEEU and the alkylvinylether/maleic acid or anhydride copolymer with the oxides and hydroxides of the alkali salts, for example, calcium, strontium, potassium, magnesium, zinc, sodium, and zirconium. When the salt is prepared, the metal compounds used, react with the carboxylic acid groups on the copolymer and neutralize them. Preferably less than

100% of the carboxylic acid groups on the copolymer chain are neutralized. More preferably, the metal compounds neutralize from the 20% to about 95% of the carboxylic acid groups of the copolymer and most preferably from about 30% to about 85% of the carboxylic acid groups.


5 In choosing the alkaline, inorganic metal compound used to neutralize the carboxylic acid groups, the anion portion of the compound is restricted, and is preferably an oxide, hydroxide, or carbonate. In general, the oxides or hydroxides are preferred because of their ease of handling, availability and the generally innocuous nature of the by-products formed in their reaction with carboxylic acids.

10 To make the salt of the invention, an aqueous dispersion of the methylvinylether/maleic anhydride copolymer and an aqueous solution of AEEU are first blended together at 25°C and held at 25°C for 20 minutes with continuous mixing, after that 20 minutes an aqueous dispersion of the metal oxides and or hydroxides is added to the AEEU, anhydride, water mixture and then the temperature is gradually raised. The  
15 dispersion of metal compounds and the AEEU-anhydride copolymer dispersion are combined and allowed to react at an elevated temperature, preferably between 50°C and 90°C. The product salt formed is dried, either in a tray or drum drier and preferably milled to less than about 100 mesh, then dispersed in a pharmacologically acceptable carrier to form the denture adhesive of this invention using techniques well known in the art.

20 MVE/MA copolymer is available from ISP Corporation in New Jersey, under the trade name GANTREZ®. The polymer is available in a GANTREZ-S series which is methyl vinyl ether/maleic acid and in GANTREZ AN series, which is methyl vinyl ether/maleic anhydride.

AEEU, which has the general structure:

25



is available from King Industries, Norwalk, Connecticut under the tradename K-Flex XM-3323.

30 The denture adhesive composition of the present invention contains a denture adhesive effective amount of the AEEU-substituted denture adhesive copolymer salt in a pharmacologically acceptable carrier. The AEEU-substituted denture adhesive copolymer

salt usually comprises from about 15% to about 55% by weight of the denture adhesive composition. Preferably it is about 25% to about 35% by weight of the denture adhesive cream composition, and most preferably from about 27% to about 33% by weight of the composition in a cream formulation and about 45% to about 55% by weight in a powder  
5 formulation.

Denture adhesives of this invention can be formulated by conventional techniques, in the form of a powder, a liquid, a cream, or a liner. The compositions also contain other active and non-active ingredients.

When the denture adhesive is formulated into a liner, the liner may be a hot-melt  
10 extruded film as described in for example, U.S. Patent No. RE33,093 to Schiraldi et al. and U.S. Patent No. 6,375,963 to Repka et al., both incorporated by reference herein. In another embodiment, the denture adhesive may be in the form of a liner, wherein the denture adhesive composition is applied to a non-adhesive-self-supporting layer, as described in, for example, U.S. Patent Nos. 4,632,880 and 4,503,116, to Lapidus and U.S. Patent No.  
15 5,880,172 to Rajaiah et al., and U.S. Patent No. 5,872,160 to Liang, all of which are incorporated herein by reference.

The active ingredient in the adhesive is the inventive metal partial salt of the AEEU-substituted MVE/MA copolymer. The AEEU degree of substitution should be between 0.05% and 0.5%, but preferably between 0.1% and 0.4%. Without being bound by theory, it  
20 is believed that the strong hydrogen bonding between the ureido group in the AEEU molecule and the peptide linkages in the oral tissues and the carbonyl groups in the acrylic polymer of the denture is responsible for the strong specific adhesion of this AEEU substituted copolymer to the gums and acrylic denture.

In addition, the adhesive agent sodium carboxymethyl cellulose gum may be added  
25 as an active ingredient. Non-active ingredients may include petrolatum, mineral oil, flavors, colors, preservatives, thickeners and a non-toxic anti-caking agent such as fumed silica.

In addition to the denture adhesive, the composition contains a pharmacologically acceptable carrier. The pharmacologically acceptable carrier contains conventional materials and if desired, may contain any additional adhesive adjuvants that have been used  
30 conventionally in the art.

For instance, the carrier may contain a carboxymethyl cellulose gum that is used for sensitizing the adhesive to moisture. When present, the cellulose gum preferably comprises from about 10% to about 38% by weight of the denture adhesive cream composition, more preferably from about 15% to about 33% and most preferably from about 20% to about 28%  
35 of the composition for a cream formula. In a powder formula, the cellulose gum preferably

comprises from about 45% to about 55% of the composition. If included in the inventive composition, the cellulose gum should be present as the full or partial alkali metal salt, preferably a sodium salt.

Non-active ingredients that may be present in the carrier portion of the denture adhesive composition include thickening agents such as petrolatum and waxes; mineral oil to provide lubricity; flavors such as synthetic flavor oils and/or oils derived from plants and fruits; colors suitable for food, drug and cosmetic use and known as FD&C colors; preservatives such as the parabens, benzoic acid, benzoates and the like; viscosity modifiers; and non-toxic and anti-caking agents such as silica, magnesium stearate and talc.

In a cream formulation, mineral oil preferably comprises from about 12% to about 17% by weight of the composition. Petrolatum is used as the thickening agent in the cream formulation by retarding the separation of the formula vehicle from the rest of the cream formula during product storage, and it preferably comprises from about 20% to about 50%, preferably from about 25% to about 45% by weight of the adhesive cream composition.

An illustrative composition of a denture adhesive cream formulation using an AEEU-substituted GANTREZ salt of the invention follows:

Ingredient	Cream Weight %	Cream Weight %
AEEU-substituted (Ca/Na 0.37%) GANTREZ <sup>®</sup> Salt	30%	30%
CMC	24%	24%
Flavorant		0.32%
Petrolatum	26.5%	27.18%
Mineral Oil	18%	18%
Preservative		
Colorants		
Gantrez Acid	1%	
Fumed Silica	0.5%	0.5%

An illustrative composition of a denture adhesive specially formulated to be compatible with a tube container and a powder formulation, using a Ca/Na 0.37% AEEU-MVE/MA salt of this invention follows:



Ingredient	Powder Weight %
<b>AEEU-substituted (Ca/Na 0.37%) GANTREZ<sup>®</sup> Salt</b>	49.84%
<b>CMC</b>	49.84%
<b>Flavorant</b>	0.32%
<b>Petrolatum</b>	
<b>Mineral Oil</b>	
<b>Preservative</b>	
<b>Colorants</b>	
<b>Fumed Silica</b>	
<b>AC Polyethylene 6A</b>	

5 The following examples are to be construed as merely illustrative and not a limitation on the scope of the invention in any way.

**EXAMPLE 1:**

10 A partial sodium, calcium AEEU salt of poly(methyl vinyl ether-co-maleic acid) (MVE/MA) was prepared by adding 3.6 g. of AEEU to 9750 g. of water at room temperature with stirring followed by adding 726.2 g. of poly(methyl vinyl ether-co-maleic anhydride) to the aqueous AEEU solution after the solution had mixed for 10 minutes. The poly(methyl vinyl ether-co-maleic anhydride) was mixed in the AEEU solution at room temperature for 20 minutes. Next 251.6 g. of calcium hydroxide was charged into the polymeric anhydride/AEEU solution at room temperature. Next a pre-mix of 18.6 g. of sodium hydroxide dissolved in 2750 g. of room temperature water was added to the calcium hydroxide/polymethyl vinyl ether maleic anhydride/AEEU mix with stirring. Next the temperature of this mixture was raised gradually to 65°C with stirring and then the temperature was held at 65°C for an additional 30 minutes after which the product was discharged, dried in a forced air oven overnight at 65°C and then the product was milled.

20 Product assay showed that this partial salt contained 0.37% AEEU, 11.6% calcium, and 0.91% sodium and 9.2% water.

The AEEU substituted partial sodium, calcium salt of poly(methyl vinyl ether maleic acid) prepared as described above was used to make a laboratory batch of denture adhesive paste (Formula B below). A control batch of adhesive was also made using unsubstituted calcium, sodium MVE/MA salt as the active (Formula A below). A third batch of adhesive paste was made with 0.5% GANTREZ Acid activator and AEEU substituted PVM/MA salt according to Formula C presented below:

	FORMULA A CONTROL	FORMULA B CONTROL	FORMULA C AEEU SALT WITH 0.5% GANTREZ <sup>®</sup> ACID FORMULA
Calcium, Sodium MVE/MA Salt	30.0		
AEEU Substituted Calcium, Sodium MVE/MA Salt		30.0	30.0
Sodium Carboxymethylcellulose	24.0	24.0	24.0
Petrolatum	27.5	27.5	27.5
Mineral Oil	18.0	18.0	18.0
Fumed Silica	0.5	0.5	0.5
GANTREZ <sup>®</sup> Acid			0.5

Paste adhesive formulas A, B, and C were tested for hang time (a measure of creep resistance), dislodge force, and subjective test performance according to the attached SOP's for these test procedures. The results of these tests are shown in Figure 1.

The results indicate that formula C tested significantly higher for dislodge force than the control formula. Both Formulas B and C tested significantly higher for hang time than Formula A. These results unexpectedly indicate that only a relatively small amount of AEEU is needed to produce a significant change in adhesive performance.

All publications, including, but not limited to, patents and patent applications cited in this specification, are herein incorporated by reference as if each individual publication

were specifically and individually indicated to be incorporated by reference herein as though fully set forth.

The above description fully discloses the invention including preferred embodiments thereof. Modifications and improvements of the embodiments specifically disclosed herein are within the scope of the following claims. Without further elaboration it is believed that one skilled in the art can, given the preceding description, utilize the present invention to its fullest extent. Therefore any examples are to be construed as merely illustrative and not a limitation on the scope of the present invention in any way. The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows.

What is claimed is:

1. A denture adhesive composition comprising a denture adhesive effective amount of a denture adhesive salt which is an amino ethyl ethylene urea- substituted mixed partial salt of a copolymer of a polyalkyl vinyl ether and maleic acid, in a pharmaceutically acceptable carrier, wherein the cations of the salt are selected from, zinc, sodium, calcium, potassium, magnesium, strontium, zirconium or combinations thereof.
2. The composition according to claim 1, wherein the cations of the partial salt are a combination of sodium, magnesium and zinc.
3. The composition according to claim 1, wherein the cations of the partial salt are a combination of magnesium and zinc.
4. The composition according to claim 1, wherein the cations of the partial salt are a combination of zinc and calcium.
5. The composition according to claim 1, wherein the cations of the partial salt are a combination of calcium and sodium.
6. The composition according to claim 1, wherein the alkyl moiety is methyl.
7. The composition according to claim 1, wherein the composition is in the form of a cream.
8. The composition according to claim 6, wherein the AEEU-substituted denture adhesive copolymer salt comprises about 15-55% by weight of the total composition.
9. The composition according to claim 1, wherein the composition is in the form of a powder.
10. The composition according to claim 1, wherein the composition is in the form of a liner.

11. The composition according to claim 10, wherein the liner is in the form of a hot-melt extruded liner.


12. The composition according to claim 10, wherein the liner is in the form of a non-adhesive self-supporting layer.

13. The composition according to claim 1, further comprising a polyalkylvinylether/maleic acid activator.

14. The composition according to claim 13, where in the polyalkylvinylether/maleic acid activator is present from about 0.1% to about 10% by weight of the composition.

13. A compound which is a mixed partial salt of an amino ethyl ethylene urea substituted polyalkylvinylether/maleic acid copolymer.

14. The compound according to claim 13, wherein the acid copolymer is neutralized with a cation selected from the group consisting of zinc, sodium, calcium, potassium, magnesium, zirconium, and strontium, or combinations thereof.

**Dislodge Force AEEU Efficacy****FIGURE 1**

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/US03/40658

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61K 6/083; C08F 8/44, 222/02

US CL : 523/120, 105; 524/558; 525/327.8, 366, 370

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

523/120, 105; 524/558; 525/327.8, 366, 370

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
EAST; gantrez, k flex, aminoethyl ethylene urea, adhesive

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4,535,122 A (SEKMAKAS et al) 13 August 1985, abstract and column 3, lines 27-44.	1-14
A	US 5,073,604 A (HOLEVA et al) 17 December 1991, abstract and examples V-VII.	1-14
A	US 5,750,591 A (CLARKE et al) 12 May 1998, abstract and examples 1-4.	1-14
A	US 6,166,102 (AHN et al) 26 December 2000, abstract and column 5, lines 1-5.	1-14

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

19 May 2004 (19.05.2004)

Date of mailing of the international search report

04 JUN 2004

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US  
Commissioner for Patents  
P.O. Box 1450  
Alexandria, Virginia 22313-1450

Facsimile No. (703) 305-3230

Authorized officer

Tae H Yoon

Telephone No. (571) 272-1700